

# Dr. Fixit Primeseal



## EFFLORESCENCE RESISTANT PENETRATING PRIMER

### Description

Dr. Fixit Primeseal is water-based primer composed of acrylic emulsion polymer, properly selected fine fillers, white pigments & additives in water as a medium. It is used as primer over exterior & interior building walls before application of Dr. Fixit Raincoat & other water based paints.

### Standard Compliance / Specification

Meets the requirement of ASTM D 1227 - 87, Type III standard.

### Areas of Application

Priming of plastered walls, asbestos, brick, false ceiling, concrete surface, etc.

### Features & Benefits

- **Bonding** - Good binding of chalky or porous substrates and over coating.
- **Suitability** - Used as a primer on internal and external surfaces.
- **Alkali resistant** - Based on chemically inert polymers hence suitable for high alkaline substrates.
- **Penetration** - Provides deep penetration thus imparts excellent substrate adhesion.
- **Efflorescence** - Provides excellent efflorescence resistance due to its chemical inertness.

### Method of Application

#### 1 SURFACE PREPARATION

- Surface for treatment must be thoroughly cleaned of all laitance, loose material, oil, grease, etc.
- Mechanical means such as wire brushing & shot blasting can be used.
- Finally vacuum cleaning of all loose solids and liquids can be done if required.
- All surface cracks up to 5 mm width should be filled up with Dr. Fixit Crack X or Dr. Fixit Unifiller. Cracks more than 5 mm and all separation gaps should be filled up with Dr. Fixit Pidicrete URP or Dr. Fixit Unibond SBR modified mortar or as specified.

#### 2 APPLICATION

- Dilute Dr. Fixit Primeseal with water in proportion of 2:1 and stir well until a uniform consistency is achieved.
- Apply a single coat of diluted Dr. Fixit Primeseal on the cleaned substrate & allow it to dry for 2 to 3 hours before commencing to further finish coats.
- Light cut with sand paper the coating of Dr. Fixit Primeseal before commencing the finish coats on internal walls

### Precautions & Limitations

- Only 50% dilution is recommended for Dr. Fixit Primeseal by water.
- Excess water on substrate must be removed by suitable means.
- Do not apply during rains or in direct sunlight.
- Do not tint the primer



## Technical Information

PROPERTIES	SPECIFICATION	RESULTS
Colour		White
Density @ 25°C, g/cc		1.28
Solid content, %		Min 48
Bonding strength		Excellent to porous substrates
Tensile strength, N/mm <sup>2</sup>	ASTM D 412	> 2.0
Efflorescence resistance		No efflorescence in paint film
Weathering resistance		Excellent

## Coverage

8-10 m<sup>2</sup> / ltr / coat

coverage may vary depending upon the nature and texture of the substrate

**Packing** 1, 4, 10 & 20 ltrs.

## Shelf Life & Storage

- Shelf life is 24 months from the date of manufacturing in unopened condition.
- Store in a cool & dry place.
- Keep away from direct sunlight

## Health & Safety Precautions

- Caution should always be exercised while handling of any chemical products.
- Skin Contact: Wash skin with soap & water. Remove contaminated clothes.
- On eye contact: Immediately splash eyes with plenty of water. Consult Physician if irritation persists.
- Ingestion: Do not induce vomiting. Never give anything by mouth to an unconscious person. Call a Physician.

## Other Products Categories available

Dr. Fixit brings you the widest range of Construction Chemicals



### Pidilite Industries Limited

Construction Chemicals Division  
 Ramkrishna Mandir Road, Post Box No. 17411  
 Andheri (E) Mumbai 400059 INDIA  
 Tel +91-22-2835 7000 • Fax +91-22-2835 7008  
 www.doctor-fixit.com • drfixitadvice@pilmail.com

Dr. Fixit Advice Centre (Toll Free No.) 1800-209-5504

**DISCLAIMER** The product information & application details given by the company & its agents has been provided in good faith & meant to serve only as a general guideline during usage. Users are advised to carry out tests & take trials to ensure on the suitability of products meeting their requirement prior to full scale usage of our products. Since the correct identification of the problems, quality of other materials used and the on-site workmanship are factors beyond our control, there are no expressed or implied guarantee / warranty as to the results obtained. The company does not assume any liability or consequential damage for unsatisfactory results, arising from the use of our products.